



RHINO GRATING

Corrosion Resistance Guide for Fiberglass Molded and Pultruded Grating

Resin type Chemical resistance Chemical type	Type V		Type I		Type O	
	Concentration %	Temperature F/°C	Concentration %	Temperature F/°C	Concentration %	Temperature F/°C
Acetic Acid	50	180/82	50	125/52	5	77/25
Aluminum Hydroxide	100	180/82	100	160/71	ALL	-
Ammonium Chloride	ALL	210/99	ALL	170/77	ALL	-
Ammonium Bicarbonate	50	160/70	15	125/52	ALL	-
Methacrylic Acid	99	95/35	-	-	-	-
Ammonium Hydroxide	28	100/38	28	N/R	ALL	N/R
Ammonium Sulfate	ALL	210/99	ALL	170/77	ALL	-
Benzene	100	92/40	ALL	N/R	ALL	N/R
Benzoic Acid	SAT	210/99	SAT	150/66	ALL	77/25
Borax	SAT	210/99	SAT	170/77	SAT	113/45
Calcium Carbide	ALL	180/82	ALL	170/77	ALL	-
Calcium Nitrate	ALL	210/99	ALL	180/82	ALL	-
Carbon Tetrachloride	100	92/40	100	N/R	100	N/R
Chlorine, Dry Gas	-	210/99	-	140/60	-	N/R
Chlorine Water	SAT	200/93	SAT	80/27	SAT	N/R
Chromic Acid	10	150/65	5	70/21	5	N/R
Citric Acid	ALL	210/99	ALL	170/77	ALL	77/25
Calcium Chloride	ALL	210/99	ALL	170/77	ALL	104/40
Copper Cyanide	ALL	210/99	ALL	170/77	ALL	77/25
Copper Nitrate	ALL	210/99	ALL	170/77	ALL	-
Ethanol	10	155/82	50	75/24	10	77/25
Ethylene Glycol	100	200/93	100	90/32	100	104/40
Hydrofluoric Acid	10	149/65	-	-	-	-
Ferric Chloride	ALL	210/99	ALL	170/77	ALL	104/40
Ferrous Chloride	ALL	210/99	ALL	170/77	ALL	86/30
Formaldehyde	37	140/60	50	75/24	25	86/30
Gasoline	100	180/82	100	75/24	100	95/35
Glucose	100	210/99	100	170/77	ALL	-
Glycerine	100	210/99	100	150/66	100	-
Hydrobromic Acid	50	150/65	50	120/49	18	-
Hydrochloric Acid	37	150/65	37	75/24	10	86/30
Hydrogen Peroxide	30	150/65	5	100/38	5	N/R
Lactic Acid	ALL	210/99	ALL	170/77	ALL	77/25
Lithium Chloride	SAT	210/99	SAT	150/66	ALL	-
Magnesium						



RHINO GRATING

Chloride	ALL	210/99	ALL	170/77	ALL	104/40
Magnesium Nitrate	ALL	210/99	ALL	140/60	ALL	86/30
Magnesium Sulfate	ALL	210/99	ALL	170/77	ALL	104/40
Mercuric Chloride	100	210/99	100	150/66	100	104/40
Mercurous Chloride	ALL	210/99	ALL	140/60	ALL	104/40
Nickel Chloride	ALL	210/99	ALL	170/77	ALL	104/40
Nickel Sulfate	ALL	210/99	ALL	170/77	ALL	104/40
Nitric Acid	20	130/54	20	70/21	20	N/R
Oxalic Acid	ALL	210/99	ALL	75/24	ALL	N/R
Perchloric Acid	30	100/38	10	N/R	10	N/R
Phosphoric Acid	100	210/99	100	120/49	80	N/R
Potassium Chloride	ALL	210/99	ALL	170/77	ALL	104/40
Potassium Dichromate	ALL	210/99	ALL	170/77	ALL	77/25
Potassium Nitrate	ALL	210/99	ALL	170/77	ALL	104/40
Potassium Sulfate	ALL	210/99	ALL	170/77	ALL	104/40
Propylene Glycol	ALL	210/99	ALL	170/77	ALL	104/40
Sodium Acetate	ALL	210/99	ALL	160/71	ALL	104/40
Sodium Bisulfate	ALL	210/99	ALL	170/77	ALL	-
Sodium Bromide	ALL	210/99	ALL	170/77	5	-
Sodium Cyanide	ALL	210/99	ALL	170/77	5	N/R
Sodium Hydroxide	25	180/82	N/R	N/R	N/R	N/R
Sodium Nitrate	ALL	210/99	ALL	170/77	ALL	104/40
Sodium Sulfate	ALL	210/99	ALL	170/77	ALL	104/40
Stannic Chloride	ALL	210/99	ALL	160/71	ALL	104/40
Sulfuric Acid	50	183/80	25	75/24	10	-
Tartaric Acid	ALL	210/99	ALL	170/77	ALL	-
Vinegar	100	210/99	100	170/77	ALL	-
Methanol	10	183/84	N/R	N/R	N/R	N/R
Sea Water	ALL	210/99	ALL	158/70	ALL	113/45
Water, Distilled	100	180/82	100	170/77	ALL	86/30
Zinc Nitrate	ALL	210/99	ALL	170/77	ALL	104/40
Zinc Sulfate	ALL	210/99	ALL	170/77	ALL	104/40

Remarks:

1. ALL refers to any concentration, SAT refers to saturated solution, N/R means not recommended and - means no information is available.

2. Tests from resin manufacturers and experiences from us indicate that the resin can withstand the corrosion conditions listed above. And the corrosion resistance data listed above is just for reference since the real environments are beyond control.